


1-27: (cancelled).

28. (previously presented): A stabilizer mixture comprising a component a) and a component e) in a weight ratio of 1:1 wherein


component a) is a product of the formula




11-14

and

component e) is a product having the structural formula



wherein R is




and wherein x is a number such that the highest number average molecular weight (osmotic method) is 3200 and the lowest number average molecular weight (osmotic method) is 2900.

**29. (new):** A stabilizer mixture comprising a component a) and a component e) in a weight ratio of 1:1 wherein

component a) is TINUVIN 622<sup>®</sup> and  
component e) is UVASORB HA 88<sup>®</sup>.

**30. (new):** A stabilizer mixture comprising a component a) and a component e) wherein

component a) is at least one compound of the formula



wherein

$\text{R}_1$  is hydrogen or methyl,

$\text{R}_2$  is a direct bond or  $\text{C}_1$ - $\text{C}_{10}$  alkylene, and

$n_1$  is a number from 2-50, and

component e) is UVASORB HA 88®

the weight ratio between component a) and component e) being from about 20:1 to about 1:20.

**31. (new):** A stabilizer mixture according to claim 30, wherein the weight ratio between component a) and component e) is 5:1 to 1:5.

**32. (new):** A stabilizer mixture according to claim 30, wherein the weight ratio between component a) and component e) is 1:1.

**33. (new):** A stabilizer mixture according to claim 30, wherein  $\text{R}_1$  is hydrogen,  $\text{R}_2$  is ethylene and  $n_1$  is a number from 2 to 25.

**34. (new):** A composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim 30.

**35. (new):** A composition according to claim 34, in which the organic material is a polyolefin.

**36. (new):** A composition according to claim 34, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.

**37. (new):** A process for stabilizing an organic material which is sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating a stabilizer mixture according to claim 30 into the organic material.

**38. (new):** A composition comprising an organic material which is sensitive to oxidative, thermal or light-induced degradation and a stabilizer mixture according to claim 33.

**39. (new):** A composition according to claim 38, in which the organic material is a polyolefin.

**40. (new):** A composition according to claim 38, in which the organic material is polyethylene, polypropylene or a copolymer of polyethylene or polypropylene.

**41. (new):** A process for stabilizing an organic material which is sensitive to oxidative, thermal or light-induced degradation, which comprises incorporating a stabilizer mixture according to claim 33 into the organic material.